

Printing date 07.08.2023

Version number 3.2 (replaces version 3.1)

Revision: 07.08.2023

GB

1 Identification of the substance/mixture and of the company/undertaking

1.1 Product identifier

- · Trade name: KREUL Acrylic gloss paint 20 ml, 50 ml, 275 ml
- · Article number:

79001, 79012, 79027, 79034, 79201, 79204, 79205, 79206, 79207, 79208, 79209, 79210, 79211, 79212, 79214, 79215, 79216, 79217, 79219, 79222, 79223, 79224, 79225, 79227, 79230, 79232, 79233, 79234, 79501, 79502, 79504, 79505, 79506, 79507, 79508, 79509, 79511, 79512, 79514, 79515, 79516, 79517, 79519, 79522, 79524, 79523, 79525, 79527, 79529, 79530, 79532, 79533, 79534, 79600, 79601 • **1.2 Relevant identified uses of the substance or mixture and uses advised against**

- 1.2 Relevant identified uses of the substance or mixture and uses advised against No further relevant information available.
- Application of the substance / the mixture
- Paint For artists and hobby user.
- 1.3 Details of the supplier of the safety data sheet
- Manufacturer/Supplier: C. KREUL GmbH & Co. KG Carl-Kreul-Straße 2 D-91352 HALLERNDORF GERMANY Phone: + 49 (0) 9545/925 - 0 Fax: + 49 (0) 9545/925 - 511 info@c-kreul.de
- Further information obtainable from: Product Safety Department: Treiber, b.treiber@c-kreul.de
 1.4 Emergency telephone number: Phone: + 49 (0) 9545/925 - 0 Fax: + 49 (0) 9545/925 - 511 (Monday - Thursday 8.00 - 17.00, Friday 8.00 - 15.00)

2 Hazards identification

2.1 Classification of the substance or mixture Classification according to Regulation (EC) No 1272/2008 The product is not classified, according to the GB CLP regulation. 2.2 Label elements · Labelling according to Regulation (EC) No 1272/2008 Void · Hazard pictograms Void Signal word Void · Hazard statements Void Additional information: Contains preservatives. EUH208 Contains BIT (1,2-benzisothiazol-3(2H)-one), C(M)IT/MIT (3:1) (reaction mass of: 5-chloro-2-methyl-4-isothiazolin-3one [EC No 247-500-7] and 2-methyl-4-isothiazolin-3-one [EC No 220-239-6] (3:1)). May produce an allergic reaction. · 2.3 Other hazards Results of PBT and vPvB assessment • PBT: Not applicable. · vPvB: Not applicable. 3 Composition/information on ingredients · 3.2 Mixtures · Description: Mixture based on water, colorants, binders and additives.

 Dangerous components: 		
	Propylene glycol substance with a Community workplace exposure limit	5-<10%
Reg.III 01-2119450609-25-7777		(Contd. on page 2)

Version number 3.2 (replaces version 3.1)

Revision: 07.08.2023

		(Contd. of page 1
	Kaolin	2.5-<5%
	substance with a Community workplace exposure limit	
CAS: 2634-33-5	BIT (1,2-benzisothiazol-3(2H)-one)	0.005-<0.05%
EINECS: 220-120-9	🛞 Acute Tox. 1, H330; 🚸 Eye Dam. 1, H318; 🚯 Aquatic Acute 1,	
	H400; Aquatic Chronic 2, H411; 🔶 Acute Tox. 4, H302; Skin Irrit.	
Reg.nr.: 01-2120761540-60-XXXX		
	Specific concentration limit: Skin Sens. 1; H317: C \ge 0.05 %	
	C(M)IT/MIT (3:1) (reaction mass of: 5-chloro-2-methyl-4- isothiazolin-3-one [EC No 247-500-7] and 2-methyl-4-isothiazolin-3- one [EC No 220-239-6] (3:1))	0.00025-<0.0015%
	% Eye Dam. 1; H318: C ≥ 0.6 % Eye Irrit. 2; H319: 0.06 % ≤ C < 0.6 % Skin Sens. 1A; H317: C ≥ 0.0015 %	

Additional information: For the wording of the listed hazard phrases refer to section 16.

4 First aid measures

· 4.1 Description of first aid measures

- After inhalation: Not applicable.
- After skin contact:

Printing date 07.08.2023

Generally the product does not irritate the skin.

Wash with water and acidic soap.

- If skin irritation continues, consult a doctor.
- After eye contact:

Remove contact lenses. Rinse opened eye for several minutes under running water.

- After swallowing:
- If symptoms persist consult doctor.

Rinse out mouth and then drink plenty of water.

- 4.2 Most important symptoms and effects, both acute and delayed No further relevant information available.
- 4.3 Indication of any immediate medical attention and special treatment needed

No further relevant information available.

5 Firefighting measures

• 5.1 Extinguishing media

- Suitable extinguishing agents: Use fire extinguishing methods suitable to surrounding conditions.
- 5.2 Special hazards arising from the substance or mixture
- Formation of toxic gases is possible during heating or in case of fire.
- 5.3 Advice for firefighters
- · Protective equipment: No special measures required.

Additional information Dispose of fire debris and contaminated fire fighting water in accordance with official regulations.

6 Accidental release measures

- 6.1 Personal precautions, protective equipment and emergency procedures Not required.
- 6.2 Environmental precautions:
- Dilute with plenty of water.
- Do not allow to enter sewers/ surface or ground water.
- 6.3 Methods and material for containment and cleaning up:
- Absorb with liquid-binding material (sand, diatomite, acid binders, universal binders, sawdust). Dispose of the material collected according to regulations.
- 6.4 Reference to other sections
- See Section 7 for information on safe handling.
- See Section 8 for information on personal protection equipment.
- See Section 13 for disposal information.

7 Handling and storage

• 7.1 Precautions for safe handling No special precautions are necessary if used correctly.

- Information about fire and explosion protection:
- No special measures required.

The product is not flammable.

(Contd. on page 3)

Version number 3.2 (replaces version 3.1)

Printing date 07.08.2023

	(Contd. of page 2)
· 7.2 Conditions for safe storage, including any incompa	tibilities
 Storage: Requirements to be met by storerooms and receptacles 	No aposial requirementa
Information about storage in one common storage facil	
· Further information about storage conditions:	
Protect from frost.	
Protect from heat and direct sunlight.	
Storage class: 12	
• 7.3 Specific end use(s) See chapter 1.2.	
8 Exposure controls/personal protection	
· 8.1 Control parameters	
Ingredients with limit values that require monitoring at	the workplace:
57-55-6 Propylene glycol	
WEL Long-term value: 474* 10** mg/m³, 150* ppm	
*total vapour and particulates **particulates	
1332-58-7 Kaolin	
WEL Long-term value: 2 mg/m ³	
· Additional information: The lists valid during the making v	vere used as basis.
· 8.2 Exposure controls	
Appropriate engineering controls No further data; see se	
Individual protection measures, such as personal prote	ective equipment
 General protective and hygienic measures: Do not eat, drink, smoke or sniff while working. 	
Avoid contact with the eyes and skin.	
Do not inhale gases / fumes / aerosols.	
Wash hands before breaks and at the end of work.	
 Respiratory protection: Not required. 	
Hand protection	a i 11a i 11a e
The glove material has to be impermeable and resistant to	
	torial can be diven for the product/ the proparation/ the chemical
	terial can be given for the product/ the preparation/ the chemical
mixture. Selection of the glove material on consideration of the pene	
mixture. Selection of the glove material on consideration of the pene Material of gloves	tration times, rates of diffusion and the degradation
mixture. Selection of the glove material on consideration of the pene Material of gloves The selection of the suitable gloves does not only depend	tration times, rates of diffusion and the degradation
mixture. Selection of the glove material on consideration of the pene Material of gloves The selection of the suitable gloves does not only depend from manufacturer to manufacturer. As the product is a	etration times, rates of diffusion and the degradation d on the material, but also on further marks of quality and varies preparation of several substances, the resistance of the glove
 mixture. Selection of the glove material on consideration of the pene Material of gloves The selection of the suitable gloves does not only depend from manufacturer to manufacturer. As the product is a material can not be calculated in advance and has therefore 	etration times, rates of diffusion and the degradation d on the material, but also on further marks of quality and varies preparation of several substances, the resistance of the glove
mixture. Selection of the glove material on consideration of the pene Material of gloves The selection of the suitable gloves does not only depend from manufacturer to manufacturer. As the product is a material can not be calculated in advance and has therefore Penetration time of glove material	etration times, rates of diffusion and the degradation d on the material, but also on further marks of quality and varies preparation of several substances, the resistance of the glove
mixture. Selection of the glove material on consideration of the pene Material of gloves The selection of the suitable gloves does not only depend from manufacturer to manufacturer. As the product is a material can not be calculated in advance and has therefore Penetration time of glove material	etration times, rates of diffusion and the degradation d on the material, but also on further marks of quality and varies preparation of several substances, the resistance of the glove e to be checked prior to the application.
 mixture. Selection of the glove material on consideration of the pener Material of gloves The selection of the suitable gloves does not only depend from manufacturer to manufacturer. As the product is a material can not be calculated in advance and has therefore Penetration time of glove material The exact break through time has to be found out by the material 	etration times, rates of diffusion and the degradation d on the material, but also on further marks of quality and varies preparation of several substances, the resistance of the glove e to be checked prior to the application.
 mixture. Selection of the glove material on consideration of the pener Material of gloves The selection of the suitable gloves does not only depend from manufacturer to manufacturer. As the product is a material can not be calculated in advance and has therefore Penetration time of glove material The exact break through time has to be found out by the material 	etration times, rates of diffusion and the degradation d on the material, but also on further marks of quality and varies preparation of several substances, the resistance of the glove e to be checked prior to the application.
mixture. Selection of the glove material on consideration of the pene Material of gloves The selection of the suitable gloves does not only depend from manufacturer to manufacturer. As the product is a material can not be calculated in advance and has therefore Penetration time of glove material The exact break through time has to be found out by the ma Eye/face protection Not required.	etration times, rates of diffusion and the degradation d on the material, but also on further marks of quality and varies preparation of several substances, the resistance of the glove e to be checked prior to the application. anufacturer of the protective gloves and has to be observed.
mixture. Selection of the glove material on consideration of the pene Material of gloves The selection of the suitable gloves does not only depend from manufacturer to manufacturer. As the product is a material can not be calculated in advance and has therefore Penetration time of glove material The exact break through time has to be found out by the material Equivalent the second sec	etration times, rates of diffusion and the degradation d on the material, but also on further marks of quality and varies preparation of several substances, the resistance of the glove e to be checked prior to the application. anufacturer of the protective gloves and has to be observed.
mixture. Selection of the glove material on consideration of the pene Material of gloves The selection of the suitable gloves does not only depend from manufacturer to manufacturer. As the product is a material can not be calculated in advance and has therefore Penetration time of glove material The exact break through time has to be found out by the ma Eye/face protection Not required. 9 Physical and chemical properties	etration times, rates of diffusion and the degradation d on the material, but also on further marks of quality and varies preparation of several substances, the resistance of the glove e to be checked prior to the application. anufacturer of the protective gloves and has to be observed.
mixture. Selection of the glove material on consideration of the pene Material of gloves The selection of the suitable gloves does not only depend from manufacturer to manufacturer. As the product is a material can not be calculated in advance and has therefore Penetration time of glove material The exact break through time has to be found out by the material Eye/face protection Not required. 9 Physical and chemical properties 9.1 Information on basic physical and chemical propert General Information Physical state Colour:	etration times, rates of diffusion and the degradation d on the material, but also on further marks of quality and varies preparation of several substances, the resistance of the glove e to be checked prior to the application. anufacturer of the protective gloves and has to be observed.
mixture. Selection of the glove material on consideration of the pene Material of gloves The selection of the suitable gloves does not only depend from manufacturer to manufacturer. As the product is a material can not be calculated in advance and has therefore Penetration time of glove material The exact break through time has to be found out by the ma Eye/face protection Not required. 9 Physical and chemical properties 9.1 Information on basic physical and chemical propert General Information Physical state Colour: Odour:	etration times, rates of diffusion and the degradation d on the material, but also on further marks of quality and varies preparation of several substances, the resistance of the glove e to be checked prior to the application. anufacturer of the protective gloves and has to be observed.
mixture. Selection of the glove material on consideration of the pene Material of gloves The selection of the suitable gloves does not only depend from manufacturer to manufacturer. As the product is a material can not be calculated in advance and has therefore Penetration time of glove material The exact break through time has to be found out by the ma Eye/face protection Not required. 9 Physical and chemical properties 9.1 Information on basic physical and chemical propert General Information Physical state Colour: Odour: Odour threshold:	etration times, rates of diffusion and the degradation d on the material, but also on further marks of quality and varies preparation of several substances, the resistance of the glove e to be checked prior to the application. anufacturer of the protective gloves and has to be observed.
 mixture. Selection of the glove material on consideration of the pener Material of gloves The selection of the suitable gloves does not only depend from manufacturer to manufacturer. As the product is a material can not be calculated in advance and has therefore Penetration time of glove material The exact break through time has to be found out by the material can not be calculated in advance. Penetration time of glove material The exact break through time has to be found out by the material can not be be protection. Physical and chemical properties 9.1 Information on basic physical and chemical propert General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing point: 	etration times, rates of diffusion and the degradation d on the material, but also on further marks of quality and varies preparation of several substances, the resistance of the glove e to be checked prior to the application. anufacturer of the protective gloves and has to be observed.
mixture. Selection of the glove material on consideration of the pene Material of gloves The selection of the suitable gloves does not only depend from manufacturer to manufacturer. As the product is a material can not be calculated in advance and has therefore Penetration time of glove material The exact break through time has to be found out by the ma Eye/face protection Not required. 9 Physical and chemical properties 9.1 Information on basic physical and chemical propert General Information Physical state Colour: Odour: Odour threshold:	etration times, rates of diffusion and the degradation d on the material, but also on further marks of quality and varies preparation of several substances, the resistance of the glove e to be checked prior to the application. anufacturer of the protective gloves and has to be observed.
 mixture. Selection of the glove material on consideration of the pener. Material of gloves The selection of the suitable gloves does not only depend from manufacturer to manufacturer. As the product is a material can not be calculated in advance and has therefore. Penetration time of glove material The exact break through time has to be found out by the material can not be be producted. 9 Physical and chemical properties 9.1 Information on basic physical and chemical propert General Information Physical state Colour: Odour threshold: Melting point/freezing point: 	etration times, rates of diffusion and the degradation d on the material, but also on further marks of quality and varies preparation of several substances, the resistance of the glove e to be checked prior to the application. anufacturer of the protective gloves and has to be observed.
 mixture. Selection of the glove material on consideration of the pener Material of gloves The selection of the suitable gloves does not only depend from manufacturer to manufacturer. As the product is a material can not be calculated in advance and has therefore Penetration time of glove material The exact break through time has to be found out by the material can not be calculated in advance. Penetration time of glove material The exact break through time has to be found out by the material can not be calculated in advance. 9 Physical and chemical properties 9.1 Information on basic physical and chemical propert General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and boiling range 	etration times, rates of diffusion and the degradation d on the material, but also on further marks of quality and varies preparation of several substances, the resistance of the glove e to be checked prior to the application. anufacturer of the protective gloves and has to be observed.
mixture. Selection of the glove material on consideration of the pene Material of gloves The selection of the suitable gloves does not only depend from manufacturer to manufacturer. As the product is a material can not be calculated in advance and has therefore Penetration time of glove material The exact break through time has to be found out by the material the exact break through time has to be found out by the material 9 Physical and chemical properties 9.1 Information on basic physical and chemical propert General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and boiling range Flammability Lower and upper explosion limit Lower:	etration times, rates of diffusion and the degradation d on the material, but also on further marks of quality and varies preparation of several substances, the resistance of the glove e to be checked prior to the application. anufacturer of the protective gloves and has to be observed.
mixture. Selection of the glove material on consideration of the pene Material of gloves The selection of the suitable gloves does not only depend from manufacturer to manufacturer. As the product is a material can not be calculated in advance and has therefore Penetration time of glove material The exact break through time has to be found out by the material the exact break through time has to be found out by the material 9 Physical and chemical properties 9.1 Information on basic physical and chemical propert General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and boiling range Flammability Lower and upper explosion limit Lower: Upper:	etration times, rates of diffusion and the degradation d on the material, but also on further marks of quality and varies preparation of several substances, the resistance of the glove e to be checked prior to the application. anufacturer of the protective gloves and has to be observed.
 mixture. Selection of the glove material on consideration of the penet Material of gloves The selection of the suitable gloves does not only depend from manufacturer to manufacturer. As the product is a material can not be calculated in advance and has therefore Penetration time of glove material The exact break through time has to be found out by the material can not be calculated in advance and has therefore Penetration time of glove material The exact break through time has to be found out by the material can not be be found out by the material Beneral Information on basic physical and chemical propert General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and boiling range Flammability Lower and upper explosion limit Lower: Upper: Flash point: 	etration times, rates of diffusion and the degradation d on the material, but also on further marks of quality and varies preparation of several substances, the resistance of the glove e to be checked prior to the application. anufacturer of the protective gloves and has to be observed.
 mixture. Selection of the glove material on consideration of the pener. Material of gloves The selection of the suitable gloves does not only depend from manufacturer to manufacturer. As the product is a material can not be calculated in advance and has therefore. Penetration time of glove material The exact break through time has to be found out by the material can not be calculated in advance and has therefore. 9 Physical and chemical properties 9.1 Information on basic physical and chemical propert General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and boiling range Flammability Lower and upper explosion limit Lower: Upper: Flash point: Decomposition temperature: 	etration times, rates of diffusion and the degradation d on the material, but also on further marks of quality and varies preparation of several substances, the resistance of the glove e to be checked prior to the application. anufacturer of the protective gloves and has to be observed.
 mixture. Selection of the glove material on consideration of the pener Material of gloves The selection of the suitable gloves does not only depend from manufacturer to manufacturer. As the product is a material can not be calculated in advance and has therefore Penetration time of glove material The exact break through time has to be found out by the material can protection Not required. 9 Physical and chemical properties 9.1 Information on basic physical and chemical propert General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and boiling range Flammability Lower: Upper: Flash point: Decomposition temperature: pH at 20 °C 	etration times, rates of diffusion and the degradation d on the material, but also on further marks of quality and varies preparation of several substances, the resistance of the glove e to be checked prior to the application. anufacturer of the protective gloves and has to be observed.
 mixture. Selection of the glove material on consideration of the pener. Material of gloves The selection of the suitable gloves does not only depend from manufacturer to manufacturer. As the product is a material can not be calculated in advance and has therefore. Penetration time of glove material The exact break through time has to be found out by the material can not be calculated in advance. 9 Physical and chemical properties 9.1 Information on basic physical and chemical propert General Information Physical state Colour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and boiling range Flammability Lower: Upper: Flash point: Decomposition temperature: pH at 20 °C Viscosity: 	etration times, rates of diffusion and the degradation d on the material, but also on further marks of quality and varies preparation of several substances, the resistance of the glove e to be checked prior to the application. anufacturer of the protective gloves and has to be observed.
 mixture. Selection of the glove material on consideration of the pener. Material of gloves The selection of the suitable gloves does not only depend from manufacturer to manufacturer. As the product is a material can not be calculated in advance and has therefore. Penetration time of glove material The exact break through time has to be found out by the material can not be calculated in advance and has therefore. Penetration time of glove material The exact break through time has to be found out by the material can not be calculated in advance and has therefore. Penetration time of glove material The exact break through time has to be found out by the material can not be calculated in advance and has therefore. Physical and chemical properties 9.1 Information on basic physical and chemical propert General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and boiling range Flammability Lower and upper explosion limit Lower: Upper: Flash point: Decomposition temperature: pH at 20 °C Viscosity: Kinematic viscosity 	etration times, rates of diffusion and the degradation d on the material, but also on further marks of quality and varies preparation of several substances, the resistance of the glove e to be checked prior to the application. anufacturer of the protective gloves and has to be observed.
 mixture. Selection of the glove material on consideration of the pener Material of gloves The selection of the suitable gloves does not only depend from manufacturer to manufacturer. As the product is a material can not be calculated in advance and has therefore Penetration time of glove material The exact break through time has to be found out by the material can protection Not required. 9 Physical and chemical properties 9.1 Information on basic physical and chemical propert General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and boiling range Flammability Lower and upper explosion limit Lower: Upper: Flash point: Decomposition temperature: pH at 20 °C Viscosity: Kinematic viscosity Dynamic: 	etration times, rates of diffusion and the degradation d on the material, but also on further marks of quality and varies preparation of several substances, the resistance of the glove e to be checked prior to the application. anufacturer of the protective gloves and has to be observed.
 mixture. Selection of the glove material on consideration of the pener Material of gloves The selection of the suitable gloves does not only depend from manufacturer to manufacturer. As the product is a material can not be calculated in advance and has therefore Penetration time of glove material The exact break through time has to be found out by the material can protection Not required. 9 Physical and chemical properties 9.1 Information on basic physical and chemical propert General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and boiling range Flammability Lower and upper explosion limit Lower: Upper: Flash point: Decomposition temperature: pH at 20 °C Viscosity: Kinematic viscosity Dynamic: Solubility 	etration times, rates of diffusion and the degradation d on the material, but also on further marks of quality and varies preparation of several substances, the resistance of the glove e to be checked prior to the application. anufacturer of the protective gloves and has to be observed.
 mixture. Selection of the glove material on consideration of the pener. Material of gloves The selection of the suitable gloves does not only depend from manufacturer to manufacturer. As the product is a material can not be calculated in advance and has therefore. Penetration time of glove material The exact break through time has to be found out by the material can not be calculated in advance and has therefore. Penetration time of glove material The exact break through time has to be found out by the material can not be calculated in advance and has therefore. Penetration time of glove material The exact break through time has to be found out by the material can not be calculated in advance and has therefore. Penetration on basic physical and chemical properties 9.1 Information on basic physical and chemical properties 9.1 Information on basic physical and chemical properties. Odour: Odour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and boiling range Flammability Lower and upper explosion limit Lower: Upper: Flash point: Decomposition temperature: pH at 20 °C Viscosity: Kinematic viscosity Dynamic: Solubility water: 	etration times, rates of diffusion and the degradation d on the material, but also on further marks of quality and varies preparation of several substances, the resistance of the glove e to be checked prior to the application. anufacturer of the protective gloves and has to be observed.
 mixture. Selection of the glove material on consideration of the pener. Material of gloves The selection of the suitable gloves does not only depend from manufacturer to manufacturer. As the product is a material can not be calculated in advance and has therefore. Penetration time of glove material The exact break through time has to be found out by the material can not be calculated in advance and has therefore. Penetration time of glove material The exact break through time has to be found out by the material can not be be protection. Not required. 9 Physical and chemical properties 9.1 Information on basic physical and chemical propert General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and boiling range Flammability Lower and upper explosion limit Lower: Upper: Flash point: Decomposition temperature: pH at 20 °C Viscosity: Kinematic viscosity Dynamic: Solubility 	etration times, rates of diffusion and the degradation d on the material, but also on further marks of quality and varies preparation of several substances, the resistance of the glove e to be checked prior to the application. anufacturer of the protective gloves and has to be observed.
 mixture. Selection of the glove material on consideration of the pener. Material of gloves The selection of the suitable gloves does not only depend from manufacturer to manufacturer. As the product is a material can not be calculated in advance and has therefore. Penetration time of glove material The exact break through time has to be found out by the material can protection Not required. 9 Physical and chemical properties 9.1 Information on basic physical and chemical propert General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and boiling range Flammability Lower and upper explosion limit Lower: Upper: Flash point: Decomposition temperature: pH at 20 °C Viscosity: Kinematic viscosity Dynamic: Solubility water: Partition coefficient n-octanol/water (log value) Vapour pressure: Density and/or relative density 	etration times, rates of diffusion and the degradation d on the material, but also on further marks of quality and varies preparation of several substances, the resistance of the glove e to be checked prior to the application. anufacturer of the protective gloves and has to be observed.
 mixture. Selection of the glove material on consideration of the pener. Material of gloves The selection of the suitable gloves does not only depend from manufacturer to manufacturer. As the product is a material can not be calculated in advance and has therefore. Penetration time of glove material The exact break through time has to be found out by the material can not be calculated in advance and has therefore. 9 Physical and chemical properties 9.1 Information on basic physical and chemical propert General Information Physical state Colour: Odour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and boiling range Flammability Lower and upper explosion limit Lower: Upper: Flash point: Decomposition temperature: pH at 20 °C Viscosity: Kinematic viscosity Dynamic: Solubility water: Partition coefficient n-octanol/water (log value) Vapour pressure: 	etration times, rates of diffusion and the degradation d on the material, but also on further marks of quality and varies preparation of several substances, the resistance of the glove e to be checked prior to the application. anufacturer of the protective gloves and has to be observed.

(Contd. on page 4)

GB

Version number 3.2 (replaces version 3.1)

Revision: 07.08.2023

	(Contd. of pa
· Vapour density	Not determined.
9.2 Other information	
Appearance:	
Form:	Fluid
Important information on protection of hea	alth and
environment, and on safety.	
Ignition temperature:	Product is not selfigniting.
· Explosive properties:	Product does not present an explosion hazard.
Change in condition	
· Evaporation rate	Not determined.
Information with regard to physical hazard class	SSES
Explosives	Void
Flammable gases	Void
Aerosols	Void
· Oxidising gases	Void
Gases under pressure	Void
Flammable liquids	Void
· Flammable solids	Void
 Self-reactive substances and mixtures 	Void
 Pyrophoric liquids 	Void
· Pyrophoric solids	Void
 Self-heating substances and mixtures 	Void
 Substances and mixtures, which emit flammab 	•
in contact with water	Void
· Oxidising liquids	Void
· Oxidising solids	Void
· Organic peroxides	Void
· Corrosive to metals	Void
 Desensitised explosives 	Void

10 Stability and reactivity

· 10.1 Reactivity No further relevant information available.

· 10.2 Chemical stability

Printing date 07.08.2023

• Thermal decomposition / conditions to be avoided: No decomposition if used according to specifications.

10.3 Possibility of hazardous reactions No dangerous reactions known.

· 10.4 Conditions to avoid No further relevant information available.

· 10.5 Incompatible materials: No further relevant information available.

· 10.6 Hazardous decomposition products: No dangerous decomposition products known.

11 Toxicological information

11.1 Information on hazard classes as defined in Regulation (EC) No 1272/2008

· Acute toxicity Based on available data, the classification criteria are not met.

۰ LD/LC50	· LD/LC50 values relevant for classification:	
2634-33-5	BIT (1,2-	benzisothiazol-3(2H)-one)
Oral	LD50	490 mg/kg (rat)
Dermal	LD50	>2,000 mg/kg (rat)
Inhalative	LC50/4h	0.05 mg/m³ (ATE)
55965-84-	• • •	MIT (3:1) (reaction mass of: 5-chloro-2-methyl-4-isothiazolin-3-one [EC No 247-500-7] and 2- 4-isothiazolin-3-one [EC No 220-239-6] (3:1))
Oral	LD50	64 mg/kg (rat)
Dermal	LD50	87 mg/kg (rab)
Inhalative	LC50/4h	0.05 mg/m³ (ATE)
· Skin corre	osion/irrit	tation Based on available data, the classification criteria are not met.
		je/irritation Based on available data, the classification criteria are not met.
		n sensitisation Based on available data, the classification criteria are not met.
		iicity Based on available data, the classification criteria are not met. used on available data, the classification criteria are not met.
		set of available data, the classification criteria are not met.
		sure Based on available data, the classification criteria are not met.
		posure Based on available data, the classification criteria are not met.
· Aspiration	n hazard l	Based on available data, the classification criteria are not met.
· 11.2 Infor	mation or	n other hazards
· Endocrine	e disrupti	ng properties
None of th	e ingredie	ents is listed.

(Contd. on page 5)

GB

Version number 3.2 (replaces version 3.1)

Revision: 07.08.2023

(Contd. of page 4)

Aquatic to:	xicity:
2634-33-5	BIT (1,2-benzisothiazol-3(2H)-one)
LC50/96h	1.6 mg/l (oncorhynchus mykiss)
EC50/48h	2.94 mg/l (daphnia magna)
EC50/72h	0.11 mg/l (selenastrum capricornutum)
EC10/72h	0.04 mg/l (selenastrum capricornutum)
ErC50/72h	0.11 mg/l (pseudokirchneriella subcapitata)
NOEC/21d	1.2 mg/l (daphnia)
NOEC/72h	0.027 mg/l (sceletonema costatum)
NOEC/28d	0.21 mg/l (oncorhynchus mykiss)
55965-84-9	C(M)IT/MIT (3:1) (reaction mass of: 5-chloro-2-methyl-4-isothiazolin-3-one [EC No 247-500-7] and 2 methyl-4-isothiazolin-3-one [EC No 220-239-6] (3:1))
LC50/96h	0.22 mg/l (oncorhynchus mykiss) (RAC)
EC50/48h	0.1 mg/l (daphnia magna)
EC50/72h	0.048 mg/l (pseudokirchneriella subcapitata)
NOEC	0.004 mg/l (daphnia magna) (OECD 211)
ErC50	0.0049 mg/l /120h (sceletonema costatum)
	0.004 mg/l (daphnia)
NOEC/48d	0.00064 mg/l (sceletonema costatum)
NOEC/72h	0.0012 mg/l (pseudokirchneriella subcapitata) (OECD 201)
NOEC/28d	0.098 mg/l (oncorhynchus mykiss) (OECD 210)
12.3 Bioac 12.4 Mobil	
12.6 Endoo 12.7 Other Additional	rine disrupting properties The product does not contain substances with endocrine disrupting properties. adverse effects ecological information:
General no	

13 Disposal considerations

· 13.1 Waste treatment methods

Recommendation

Small amounts may be diluted with plenty of water and washed away. Dispose of bigger amounts in accordance with Local Authority requirements.

- · Uncleaned packaging:
- · Recommendation: Disposal must be made according to official regulations.
- · Recommended cleansing agents: Water, if necessary together with cleansing agents.

not regulated	
not regulated	
not regulated	
not regulated	
Not applicable.	
Not applicable.	
to IMO Not applicable.	
	not regulated not regulated not regulated Not applicable. Not applicable. to IMO

Version number 3.2 (replaces version 3.1)

Revision: 07.08.2023

(Contd. of page 5)

· UN "Model Regulation":

Printing date 07.08.2023

not regulated

15 Regulatory information

15.1 Safety, health and environmental regulations/legislation specific for the substance or mixture

· Directive 2012/18/EU

- Named dangerous substances ANNEX I None of the ingredients is listed.
- 15.2 Chemical safety assessment: A Chemical Safety Assessment has not been carried out.

16 Other information

This information is based on our present knowledge. However, this shall not constitute a guarantee for any specific product features and shall not establish a legally valid contractual relationship.

Relevant phrases

- H301 Toxic if swallowed.
- H302 Harmful if swallowed.
- H310 Fatal in contact with skin.
- Causes severe skin burns and eye damage. H314
- H315 Causes skin irritation.
- H317 May cause an allergic skin reaction.
- H318 Causes serious eye damage.
- H330 Fatal if inhaled.
- H400 Very toxic to aquatic life.
- H410 Very toxic to aquatic life with long lasting effects.
- H411 Toxic to aquatic life with long lasting effects.
- EUH071 Corrosive to the respiratory tract.

· Department issuing SDS: Product Safety Department

Contact: B. Treiber, b.treiber@c-kreul.de

Abbreviations and acronyms:

ADR: Accord relatif au transport international des marchandises dangereuses par route (European Agreement Concerning the International Carriage of Dangerous Goods by Road) IMDG: International Maritime Code for Dangerous Goods

- IATA: International Air Transport Association GHS: Globally Harmonised System of Classification and Labelling of Chemicals
- EINECS: European Inventory of Existing Commercial Chemical Substances ELINCS: European List of Notified Chemical Substances CAS: Chemical Abstracts Service (division of the American Chemical Society)
- LC50: Lethal concentration, 50 percent LD50: Lethal dose, 50 percent
- PBT: Persistent, Bioaccumulative and Toxic vPVB: very Persistent and very Bioaccumulative Acute Tox. 3: Acute toxicity Category 3 Acute Tox. 4: Acute toxicity Category 4

- Acute Tox. 2: Acute toxicity Category 2 Acute Tox. 1: Acute toxicity Category 1 Skin Corr. 1C: Skin corrosion/irritation Category 1C
- Skin Irrit. 2: Skin corrosion/irritation Category 2 Eye Dam. 1: Serious eye damage/eye irritation Category 1
- Skin Sens. 1: Skin sensitisation Category 1 Skin Sens. 1A: Skin sensitisation Category 1A
- Aquatic Acute 1: Hazardous to the aquatic environment acute aquatic hazard Category 1 Aquatic Chronic 1: Hazardous to the aquatic environment long-term aquatic hazard Category 1 Aquatic Chronic 2: Hazardous to the aquatic environment long-term aquatic hazard Category 2
- * Data compared to the previous version altered.

GB